

# NovaForm™ PVC Liner

## Product Data Sheet



### < STANDARDS >



ASTM D638  
ASTM D648  
ASTM D790  
ASTM D1784  
ASTM D2122  
ASTM D2152  
ASTM D2412  
ASTM D2444  
ASTM F1057  
ASTM F1504  
ASTM F1947

## introduction

NovaForm™ PVC Liner is used in sewer and culvert rehabilitation. Extruded and coiled onto reels, the product is heated and conditioned on the job site, then pulled into an existing sewer or culvert by mechanical means. The NovaForm Liner is plugged and expanded by introducing steam and then air, allowing it to form snugly against the host pipe. As air is introduced, the pipe cools and hardens producing a fully functional pipe.

### PRODUCT AVAILABILITY

Material	PVC
Size Range	6" – 30" (150mm – 750mm)

### Sample Specification

This specification covers requirements and test methods for materials, dimensions, workmanship, flattening resistance, impact resistance, pipe stiffness, extrusion quality, marking and packaging.

### Material Specification

#### Basic Materials

The pipe shall be made from PVC compound meeting all the requirements for cell classification 12334 as defined in specification D1784 and with minimum flexural modulus properties, tested as per ASTM Method D790, of 320,000psi (2,200MPa).

<b>Tensile Strength</b>	Test Method D638	6,000 psi	(41.4 MPa)
<b>Tensile Modulus</b>	Test Method D638	320,000 psi	(2,206 MPa)
<b>Flexural Strength</b>	Test Method D790	6,000 psi	(41.4 MPa)
<b>Flexural Modulus</b>	Test Method D790	320,000 psi	(2,206 MPa)
<b>Heat Deflection Temperature (tested @ 264psi)</b>	Test Method D648	158°F	(70°C)

### Other Requirements

#### Pipe Flattening

There shall be no evidence of splitting, cracking or breaking when the rounded pipe is tested according to section 11.3 of ASTM F1504.

#### Pipe Impact Strength

The impact strength of rounded pipe shall not be less than the values in Table 1 when tested in accordance with test method D2444 as referenced in ASTM F1504.

**Table 1: Minimum Impact Strength at 73°F (23°C)**

Pipe size, in. (mm)	Impact strength, ft-lbf (J)
6 (150)	210 (284)
8 (200)	210 (284)
10 (250)	220 (299)
12 (300)	220 (299)
15 (375)	220 (299)
18 (450)	220 (299)
24 (600)	220 (299)
30 (750)	220 (299)

### Pipe Stiffness

Values for pipe stiffness for the rounded pipe shall comply with Table 2 when tested in accordance with test method D2412 as referenced in ASTM F1504.

**Table 2: Minimum Pipe Stiffness at 5% Deflection**

Pipe Size, in. (mm)	Pipe Stiffness, psi (kPa)	Dimension Ratio, (DR)
6 (150)	36 (250)	35
8 (200)	36 (250)	35
10 (250)	36 (250)	35
12 (300)	22 (153)	41
15 (375)	12 (83)	50
18 (450)	6 (41)	66
24 (600)	6 (41)	66
30 (750)	6 (41)	66

### Extrusion Quality

The extrusion quality of the pipe shall be evaluated by both of the following test methods:

**Acetone Immersion:** The pipe shall not flake or disintegrate when tested in accordance with test method D2152 as referenced in ASTM F1504.

**Heat Reversion:** The extrusion quality of the pipe shall be estimated by heat reversion method in accordance with practice F1057 as referenced in ASTM F1504.

**Flexural Properties:** The flexural strength and modulus of the pipe shall be tested in accordance with test method D790 as referenced in ASTM F1504.

### Dimensions

**Rounded Pipe Diameter:** The average outside diameter of the formed pipe shall meet requirements in Table 3, +/- 1.0% when tested in accordance with test method D2122 as referenced in ASTM F1504.

**Rounded Pipe Wall Thickness:** The wall thickness of the formed pipe shall not be less than the values specified in Table 3 when tested in accordance with test method D2122 as referenced in ASTM F1504.

**Table 3 Rounded Pipe Dimensions**

Nominal Outside Diameter In. (mm)	Minimum Wall Thickness		DR
	In. (mm)	In. (mm)	
6 (150)	0.17	(4.3)	35
8 (200)	0.23	(5.8)	35
10 (250)	0.28	(7.3)	35
12 (300)	0.29	(7.4)	41
15 (375)	0.30	(7.6)	50
18 (450)	0.27	(6.8)	66
24 (600)	0.34	(8.7)	66
30 (750)	0.43	(10.8)	66

### Workmanship, finish, and appearance

The rounded and folded pipes shall be homogeneous throughout and free from visible cracks, holes, foreign inclusions, or other defects. The pipe shall be as uniform as commercially possible in colour, opacity, density and other physical properties.

### Product Marking

Pipe shall be clearly marked as follows at intervals of 5ft. (1.5m) or less:

- Manufacturer's name or trademark and code
- Nominal outside diameter
- The PVC cell classification, for example "12334"
- The legend "DR XX FOLDED PVC PIPE"
- The designation "Specification ASTM F1504"
- Length marker and liner distance label, for example "100ft" ("30.5m")

### Packaging

The full length of the PVC pipe is coiled onto a reel in a continuous length for storage and shipment. The minimum diameter of the reel drum or core shall be 48in.

### Quality Assurance

When the product is marked with ASTM F1504 designation, the manufacturer affirms that the product was manufactured, inspected, sampled and tested in accordance with the specification and has been found to meet the requirement of it.

## Installation

The NovaForm PVC Liner should be installed in accordance with ASTM F1947 and the installation instructions below. For complete installation instructions, please consult the NovaForm Training Manual available at [ipexna.com](http://ipexna.com).

### 1. Preparing

For any lining technology, host pipe preparation is key to a successful installation.

This step is common to many rehabilitation technologies and involves common practices such as:

- Identifying any conditions in the existing host pipe that could impede or prevent the proper installation of the liner.
- Accurately recording the position of all service connections.
- Remediating large quantities of groundwater infiltration, roots, collapsed pipe, dropped joints or offsets more than 12.5% of the inside pipe diameter, protruding taps, amongst other common defects.
- Cleaning/Flushing the line
- Bypass control (if required)
- Traffic Control (if required)

For more information on these preparatory works, industry associations such as NASSCO should be consulted for more information.

### 2. Conditioning

Prior to pulling the NovaForm PVC Liner into the existing host pipe, it first must be softened to allow it to be pulled from the shipping reel. This is typically accomplished by applying steam to the product until heated thoroughly. Infrared thermal guns allow the installer to monitor the temperature of the product during this stage.

### 3. Pulling

In order to process the NovaForm PVC Liner, it first must be pulled into place. This is typically accomplished through mechanical means by using a winch. A cable from the winch is fed from the downstream manhole (“B” side) to the upstream manhole (“A” side) and attached to the end of the NovaForm PVC Liner. It is then pulled into place using a series of rollers until it reaches the downstream manhole.

### 4. Processing

Once in place, NovaForm PVC Liner is processed. Processing generally involves the following steps:

- The conditioning of pipe ends (“A” and “B” sides) in order to insert plugs which allow the passage of steam and air through the product.
- Additional conditioning throughout the entire product length in order to ensure the product is heated sufficiently to allow for expansion.
- Product expansion by increasing the steam pressure in the line, gradually.
- Transition to air to complete the expansion process and cool the liner. Once sufficiently cooled, the product hardens and processing is completed.

### 5. Finishing

Finishing involves the reinstatement of service connections and trimming of the liner ends. This step is performed with the aid of CCTV inspection and robotic cutters. Common to many lining technologies, additional details on the finishing phase of the NovaForm PVC Liner installation process can be found through industry associations such as NASSCO.

### About the IPEX Group of Companies

As leading suppliers of thermoplastic piping systems, the IPEX Group of Companies provides our customers with some of the world's largest and most comprehensive product lines. All IPEX products are backed by more than 50 years of experience. With state-of-the-art manufacturing facilities and distribution centers across North America, we have established a reputation for product innovation, quality, end-user focus and performance.

Markets served by IPEX group products are:

- Electrical systems
- Telecommunications and utility piping systems
- Industrial process piping systems
- Municipal pressure and gravity piping systems
- Plumbing and mechanical piping systems
- Electrofusion systems for gas and water
- Industrial, plumbing and electrical cements
- Irrigation systems
- PVC, CPVC, PP, PVDF, PE, ABS, and PEX pipe and fittings

Products are manufactured by IPEX Inc. and distributed in the United States by IPEX USA LLC.

NovaForm™ is a trademark of IPEX Branding Inc.

This literature is published in good faith and is believed to be reliable. However, it does not represent and/or warrant in any manner the information and suggestions contained in this brochure. Data presented is the result of laboratory tests and field experience.

A policy of ongoing product improvement is maintained. This may result in modifications of features and/or specifications without notice.

